1 TITLE OF THE INVENTION
2 CEMENTITIOUS COMPOSITIONS AND CEMENTITIOUS SLURRIES
3 FOR PERMANENTLY PLUGGING ABANDONED WELLS AND
4 PROCESSES AND METHODS THEREFOR

5 CROSS-REFERENCE TO RELATED APPLICATIONS
6 This application claims the benefit of the priority of
7 U.S. Provisional Application Serial No. 60/244,330, filed
8 October 30, 2000 and entitled "CEMENTITIOUS COMPOSITIONS AND
9 CEMENTITIOUS SLURRIES FOR PERMANENTLY PLUGGING ABANDONED
10 WELLS AND PROCESSES AND METHODS THEREFOR."

11 BACKGROUND
12 Wells of various types after their useful lives are
13 shut down and usually permanently plugged for a variety of
14 reasons. Frequently, depleted hydrocarbon producing wells
15 are required by laws to be permanently plugged for
16 protecting aquifers and the above surface environment.
17 Regulations exist for plugging abandoned wells to
18 protect both below and above surface environments and to
19 prevent accidents from occurring at the plugged well. Such
20 regulations often require that the plugs have a certain
21 minimum strength and maximum liquid permeability.
22 Governmental agencies often are required to inspect and
23 approve hydrocarbon well closures before the wells can be
24 officially certified as closed. For example, in the State
25 of California the certifying agency is the Department of
26 Conservation, Division of Oil and Gas.
27 Although approved well-closure compositions exists,
28 since permanently plugged wells are no longer a source of
29 income, there is a strong economic incentive to permanently
30 plug such wells as cheaply as possible. This invention is

- 1 -

directed to cheaper cementitious compositions for permanently plugging wells, processes of preparation of such compositions, processes for applying such compositions, and methods having advantages of reducing the costs of such operations including estimating cost and markup or bid prices.

In the abandonment of hydrocarbon wells, hydraulic cementitious slurries are used to create hard plugs in the wellbore which are effective for permanently closing the well. Specialized equipment is used to inject the slurry into the well at surface level. Under pressure the slurry is forced to the bottom of the well and into the subterranean porosity zone. As the slurry fills in at the well bottom, sufficient resistance is met to cause the slurry to lift vertically towards the surface. Based on the diameter and depth of a given well, the volume of hydraulic cementitious slurry required to close a particular well can be calculated. The slurry must produce upon curing a vertical hard plug to a level of 100 ft. above the subterranean porosity zone.

The performance of a given slurry mix for hydrocarbon well closure is required to meet the American Petroleum Institute ("API") specification for a competent hard plug. As defined by API, a hard plug must meet and maintain a compressive strength of 1000 psi and have a maximum permeability of 0.1 millidarcy ("md").

Many hydrocarbon production companies contract well abandonment work to service organizations that specialize in well closure services. These service organizations use approved cementitious materials in the slurry mixes for placing and forming the competent hard plugs. G series Portland cement and minus 200 sieve silica product are

- 2 -

currently approved materials for well plug slurries. By the term "silica product" as used herein is meant a solid material whose major component is silica and is widely used in hydraulic cements. Generally in such silica products the amount of silica exceeds about 95% and is usually about 98% to about 99%. As used herein, the term silica product does not included cement kiln dust ("CKD"). These materials are relatively high cost products individually when compared to the dry cementitious solids of this invention. A typical silica product suitable for forming hydraulic cementitious slurries is from about minus 90 mesh silica sand to about minus 200 mesh silica powder.

In current conventional well abandonment operations, G Series Portland cement is obtained from cement manufacturers and the silica product from other manufacturers at other locations. Transportation cost from two different locations are incurred. Before the cement and silica product are used to form the hydraulic cementitious slurry they must be blended, and thereafter slurried with water, before pumping down the well, as illustrated in FIG. 1.

SUMMARY

Accordingly, this invention is directed to less costly dry cementitious solids for slurry use and a process for blending such dry cementitious solids which have the advantage of greatly reducing the cost of hydrocarbon well abandonment and closing.

In general this invention is directed towards dry cementitious solids comprising cement kiln dust ("CKD") and cement: hydraulic cementitious slurries produced from such dry cementitious solids; the solid cementitious compositions

resulting from the curing of such hydraulic cementitious slurries; processes for making and using such materials; methods of blending the dry cementitious solids prior to slurrying; and methods for estimating and reducing cost and estimating price markup in well closure operations using the CKD-containing formulations of this invention.

CKD is a waste material generated in cement manufacture. CKD is a partially calcined kiln feed which is removed from the gas stream and collected in a dust collector. Chemical analysis of CKD from cement manufacturers usually varies depending on the particular feed. Variations also exist from one manufacture to another depending in part on the efficiencies of the cement production operation and the associated dust collection systems. Typically, the major oxides found in CKD's are SiO_2, Al_2O_3, Fe_2O_3, CaO, MgO, SO_3, Na_2O and K_2O. Chemical analysis of some CKD's are found in U.S. Patent Nos. 4,432,800 and Re.33,747 which are hereby incorporated herein by reference. Such variations, however, do not have any detrimental effects on the usefulness and performance of this invention.

CKD is available from a number of cement manufacturers at a price significantly lower than the cost of materials currently being used in cementitious slurries for hydrocarbon well closures. Type II Portland cement is cheaper than G Series Portland cement by about $2.00 per ton based on raw cost. Since the resulting hard cores produced by this invention using Type II Portland cement meet or exceed all requirements of API for a competent hard plug, Type II Portland cement is preferred only for achieving better economics. Of course, if desired the more expensive

- 4 -

1   G Series Portland cement can also be used. In fact, any
2   type of cement can be used in this invention.

3   In the economics of hydrocarbon abandonment service
4   contracts, the profits are determined by a charged cost per
5   cubic foot ("cf") of slurry, which in turn is determined by
6   the choice of materials, the transportation cost, and the
7   blending cost. This invention is also directed to processes
8   for reducing the cost of well closures.

9   CKD is made available by a number of cement
10   manufactures so that both the CKD and the cement can be
11   obtained from the same source essentially at the same source
12   location thereby reducing transportation cost. CKD is often
13   regarded as a waste product of the cement industry having
14   limited use elsewhere.

15   BRIEF DESCRIPTION OF THE DRAWINGS
16   FIG. 1 is a flow diagram for a process for producing a
17   blended cementitious slurry of cement and silica into an
18   abandoned well.

19   FIG. 2 is a flow diagram for a process for producing a
20   hydraulic cementitious slurry formed from a cement-CKD blend
21   into an abandoned well.

22   FIG. 3 is a flow diagram for a method of determining a
23   markup price for providing a cement-CKD blend to an off-load
24   site.

25   FIG. 4 is a flow diagram for a process for producing
26   and transporting a cement-CKD blend to an off-load site.

27   FIG. 5 is a flow diagram for a process for producing
28   and transporting a cement-CKD blend to an off-load site and
29   for closing a well.

PREFERRED EMBODIMENTS

1

2   FIG. 2 illustrates one embodiment of this invention

3   producing a slurry effective for injection into an abandoned

4   well intended to be closed.

5   In this invention blending of the dry cementitious

6   solids is achieved by loading in a suitable transporting

7   container a predetermined weight of CKD and, thereafter,

8   loading in the same container, a predetermined weight of

9   cement on top of the CKD. The amount of CKD and cement

10 corresponds to a predetermined ratio of such dry

11 cementitious solids.   In other words, the loaded dry

12 cementitious solids in the container have the predetermined

13 weight ratio of "cement/CKD" required for preparing the

14 final hydraulic cementitious slurry by merely adding water

15 and slurrying for use in a particular well.

16   In one embodiment of this invention, blending of the

17 dry cementitious solids is accomplished automatically during

18 transportation at no additional cost by taking advantage of

19 the different specific gravities and bulk densities of CKD

20 and cement.   For example, Type II Portland cement has a

21 specific gravity ("SG") of about 3.14 and a bulk density of

22 about 94 lbs/cf. On an average CKD has a SG of from about

23 2.6 to about 2.9 and a bulk density of from about 48 to

24 about 55 lbs/cf. The CKD variations result from differences

25 in raw kiln feed, cement production efficiencies and

26 associated CKD collection systems that exist from one cement

27 manufacturer to another and from one kiln to another kiln of

28 the same cement manufacturer. Such CKD variations do not

29 have any detrimental effects that prevent their use in this

30 invention.

31   The particle size of both the cement and CKD are in a

32 range of from about 300 to about 325 sieve mesh. On average

transportation of the dry cementitious solids will be in the
range of 50 to 100 miles as measured from the cement source
site to the off-load site. Normal vibration generated
during such travel will cause some of the heavier density
cement to work its way down in the container thereby
displacing some of the lighter density CKD and causing the
CKD to rise, thereby blending the materials in the container
automatically while in transit sufficiently for slurrying
with water without further blending after off-loading.
Pneumatic off-loadable trucks and railroad cars, for
example, have containers suitable for transportation of such
dry cementitious solids. Just prior to off-loading the dry
cementitious solids the containers are aerated or purged to
remix any concentration of cement in the bed of the
container.

In this invention, the blending of CKD and cement,
preferably Type II Portland cement, in specific ratios, when
slurried with water in predetermined amounts, will produce a
variety of slurries that will achieve a compressive strength
at least of 1000 psi and meet or exceed all requirements of
API for a competent hard plug.

Accordingly, there is provided by the principles of
this invention, novel cementitious compositions and
hydraulic cementitious slurries using CKD as one of the
major components thereof.

In one embodiment of this invention, the cement is Type
II Portland cement, however, any type of cement can be used
if desired.

In another embodiment of this invention, the CKD has at
least about 10% free lime as determined by analysis. All
percents herein, unless otherwise specified, are weight

- 7 -

1 percents. By the term "free lime" as used herein is meant
2 calcium existing in the form of calcium oxide, i.e. CaO.

3 In still another embodiment of this invention, the CKD
4 has at least about 40% CaO as determined by analysis on an
5 oxide basis.

6 In one embodiment of this invention, a dry cementitious
7 composition is provided, which when slurried with water, is
8 effective for permanently plugging a well. The dry
9 cementitious composition comprises CKD and cement as the
10 major components. In a further embodiment, the CKD is at
11 least about 40% by weight of the dry cementitious
12 composition. In another further embodiment, the cement is
13 at least about 40% by weight of the dry cementitious
14 composition.

15 In another embodiment, the dry cementitious composition
16 is about 50% by weight CKD, and about 50% by weight cement.

17 In still another embodiment, the dry cementitious
18 composition is about 60% by weight CKD and about 40% by
19 weight cement.

20 In one embodiment of this invention, a dry cementitious
21 composition is provided which comprises cement and CKD as
22 major components and which also has a weight ratio of parts
23 of cement to parts of CKD between about 2/3 and 3/1.

24 In further embodiment, the dry cementitious composition
25 is at least about 70% by weight cement and CKD. In a still
26 further embodiment, the dry cementitious composition is at
27 least about 90% by weight cement and CKD.

28 In further embodiment, the dry cementitious composition
29 has a weight ratio of parts of cement to parts of CKD
30 between about 2/3 and about 7/3, and preferably between
31 about 2/3 and about 3/2.

- 8 -

1   In hot wells, to prevent boiling of the hydraulic
2   cementitious slurry, the slurry can also contain a
3   predetermined amount of silica flour. Silica flour is fine
4   silica, generally
5   about minus 325 mesh.

6   In a further embodiment, the dry cementitious
7   composition also contains silica flour. In a still further
8   embodiment, the dry cementitious composition has a weight
9   ratio of parts of silica flour to parts of cement of from
10   about 0.30 to about 0.40.

11   In the cement industry, the unit weight of dry cement
12   and cementitious materials is a "sack." A sack is defined
13   as 94 lbs. of dry cementitious material. Thus a sack can
14   contain only cement, or a mixture of cement and CKD, or a
15   mixture of any other cementitious formulation.

16   Examples of the formulations of three embodiments of
17   this invention are shown in Table I. Tested hard plugs
18   produced by this invention in accordance with the
19   formulations in Table I, meet or exceed API specifications.

20   Table I

21 Formulation	A	B	C
22 Dry cementitious materials:			
23 % cement	40	50	60
24 % CKD	60	50	40
25 Gallons of water per sack:	6.5	8	10

26   Table II illustrates load data of laboratory tested
27   cores prepared from formulations of this invention, where
28   CKD and cement from Source I of Table IV have been used to

1 prepare hard cores. Tests of the hard cores in Table II
2 were conducted in accordance with ASTM C-39 specification.

3 Table II shows that the compressive strengths of cured
4 samples produced by this invention increases with curing
5 time. In these examples, the SG of the Type II Portland
6 cement was 3.14 and the SG of the CKD was 2.8.

7 Yield ("Y") is the cubic feet of slurry produced per
8 sack of cementitious material after slurrying with a
9 predetermined amount of water. In this case the sack is a
10 94 lb mixture of cement and CKD. Density of the slurry is
11 usually expressed in lb/cf. Usually both yield and density
12 are calculated. The calculated yield is the sum of the
13 volumes of each component per sack which at ambient
14 conditions is equal to

$$15,16,17 \quad 0.01506 \times \left(\frac{\% \text{ cement}}{\text{SG cement}} + \frac{\% \text{ CKD}}{\text{SG CKD}} \right) + 0.1337 \times (\text{gal. of water}) \qquad \text{Eq. 1}$$

18 The calculated density ("D") is the sum of the weights
19 of each component per sack divided by the sum of the volumes
20 of each component per sack, which is equal to

$$21 \quad (94 \text{ lb} + \{8.337 \times (\text{gal. of water})\}) / Y \qquad \text{Eq. 2}$$

22 Payment is usually based on the number of cubic feet of
23 slurry used for a well closure operation. Therefore, for a
24 given load and compressive strength requirement for closure
25 of a given well, the cementitious slurry which is the
26 cheapest per cf, while still meeting particular requirements
27 for the well, is economically advantageous for a well
28 closure operation. The cementitious slurry which is the

1   cheapest includes the cost of the cementitious composition
2   from the cement manufacturer, the cost of blending, and the
3   cost of transportation and off-loading at the off-loading
4   site. In this invention, however, there is no cost of
5   blending since blending of the cement and CKD is achieved
6   automatically during transit from the cement manufacture to
7   the off-load site. Both sack cost and yield are factors in
8   determining the cementitious composition cost. This
9   invention also provides a method of estimating such cost and
10 markup prices.

11 Table III is an example of the yields and densities of
12 typical prior art formulations using G Series Portland
13 cement and silica product as the cementitious materials
14 which when mixed with water produced a cementitious slurry
15 which meets API specifications. In this example the SG of
16 the G Series Portland cement is 3.15 and the SG of the
17 silica product is 2.65. The bulk density of the G Series
18 Portland cement is 94 lb/cf and the bulk density of the
19 silica product is 74 lb/cf. The typical cost per cf of just
20 the raw ingredients, i.e. exclusive of transportation and
21 blending, is estimated to range from about $1.06 to about
22 $1.55.

23 Table IV shows the chemical analysis on a major oxide
24 bases of several typical CKD by different cement
25 manufacturers. This data was supplied by Sources I, II and
26 III, and taken from U.S. Patent No. 4,432,800 for Sources
27 IV, V and VI. Slurries produced by this invention using the
28 CKD from these sources will meet or exceed API
29 specifications. Although almost any CKD from any cement
30 manufacturer can be used in this invention with adjustment
31 of the cement to CKD ratio, CKD from some sources will be

1 preferred over others depending on the particular chemistry
2 of the CKD and/or the cost of transportation.

3   There is also provided by the principles of this
4 invention a method for determining a price for providing a
5 mixture of CKD and cement to a well site comprising
6 determining the cost of CKD and cement at a manufacturer's
7 site, determining the cost of transportation of the mixture
8 from the same manufacturer's site to an off-load site,
9 determining the total slurry cost of providing the mixture
10 of CKD and cement to the off-load site, and determining a
11 markup price for the mixture off-loaded at the off-load site
12 as illustrated in FIG. 3.

13   There is also provided by the principles of this
14 invention a process of forming a blended mixture of CKD and
15 cement comprising adding CKD to a container suitable for
16 shipping cementitious materials from a manufacturer's site
17 to an off-load site, thereafter, adding cement to the same
18 container on top of the cement at the same manufacturer's
19 site, and transporting the cementitious materials in the
20 container to the off-load site while allowing natural
21 vibration during the transporting to blend the CKD and
22 cement as illustrated in FIG. 4.

23   There is also provided by the principles of this
24 invention a process for closing a well comprising providing
25 a mixture of CKD and cement at a well site, slurrying the
26 mixture of CKD and cement with water, pumping a sufficient
27 amount of the slurry down the well to fill the well, and
28 curing the mixture in the well to form a cementitious
29 competent hard plug in the well as illustrated in FIG. 5.

30   Accordingly, as illustrated in FIG. 6, there is also
31 provided by the principles of this invention a method of
32 determining a lowest cost per unit volume of a hydraulic

1 cementitious slurry comprising determining cost of procuring
2 a cement and a CKD in a predetermined weight ratio of cement
3 to CKD at and from a cement source. Then determining yields
4 of hydraulic cementitious slurries formed by slurrying a dry
5 cement-CKD blend having the predetermined weight ratio of
6 cement to CKD with various amounts of water.

7 Then determining which of the hydraulic cementitious
8 slurries when cured over a predetermined period of time will
9 meet or exceed a predetermined specification, and then
10 determining a hydraulic cementitious slurry having a lowest
11 cost per unit volume using the dry cement-CKD blend and
12 which meets or exceeds the predetermined specification.

13 In a further embodiment, the method also includes
14 determining a cost for supplying the dry cement-CKD blend
15 from the cement source to an off-load site using the
16 hydraulic cementitious slurry determined to have the lowest
17 cost per unit volume and which meets or exceeds the
18 predetermined specification.

19 In another further embodiment, the method includes
20 repeating the above determinations for other ratios of
21 cement to CKD. For example, determining cost of procuring
22 the cement and the CKD in another predetermined weight ratio
23 of cement to CKD at and from the same cement source. Then
24 determining yields of hydraulic cementitious slurries formed
25 by slurrying a dry cement-CKD blend having the new
26 predetermined weight ratio of cement to CKD with various
27 amounts of water.

28 Then determining which of the hydraulic cementitious
29 slurries when cured over a predetermined period of time will
30 meet or exceed the same predetermined specification, and
31 then determining a hydraulic cementitious slurry having a
32 lowest cost per unit volume using the new dry cement-CKD

- 13 -

blend and which meets or exceeds the predetermined specification. At this stage in the method the lowest cost hydraulic cementitious slurry has been determined for slurries with two cement-CKD blends from the same sort but with different ratios of cement to CKD. Unless there are other factors to consider, the method now calls for selecting the cement-CKD blend which results in the lowest cost for producing a hydraulic cementitious slurry which meets or exceeds the predetermined specification.

The method can be repeated for yet another cement-CKD blend having another ratio of cement to CKD. For example, three dry cement-CKD blend which are particularly useful are 2/3, 1/1 and 3/2 parts of cement to parts of CKD where the hydraulic cementitious slurry to be produced is to be used for closing wells. This invention, however, is not limited just to the closing of wells and other uses of the hydraulic cementitious slurries of this invention can of course be used for different purposes. Such other purposes can have different specifications for the resulting cured product.

While the preferred embodiments of the present invention have been described, various changes, adaptations and modifications may be made thereto without departing from the spirit of the invention and the scope of the appended claims. The present disclosure and embodiments of this invention described herein are for purposes of illustration and example and modifications and improvements may be made thereto without departing from the spirit of the invention or from the scope of the claims. The claims, therefore, are to be accorded a range of equivalents commensurate in scope with the advances made over the art.

TABLE II
MATERIAL BLENDS FOR SP 50 SLURRY MIX

CEMENT	CKD	WATER	DENSITY	COMPRESSIVE STRENGTH IN PSI				YIELD	COST
				24 HOUR	7 DAY	14 DAY	28 DAY		
70%	30%	10	97.41	ND	ND	ND	ND	1.82	$1.31
60%	40%	6.5	108.14	1310	2740	ND	ND	1.37	$1.55
60%	40%	7	105.77	1270	2480	ND	ND	1.44	$1.47
60%	40%	8	102.31	ND	ND	ND	1340	1.57	$1.35
60%	40%	9	99.39	510	1180	ND	1270	1.7	$1.24
60%	40%	10	96.88	ND	670	ND	1080	1.83	$1.16
50%	50%	6.5	107.35	1095	2130	ND	ND	1.38	$1.33
50%	50%	8	102.32	ND	ND	ND	1240	1.57	$1.16
40%	60%	7	105.04	ND	ND	ND	1430	1.45	$1.06
40%	60%	8	101.67	ND	ND	ND	ND	1.58	$0.98

WATER IS GALLONS PER 94 Lb. SACK
DENSITY IS POUNDS PER CUBIC FOOT
COMPRESSIVE STRENGTH RESULTS - ASTM C 39 TEST
YIELD IS NET VOLUME IN CUBIC FEET FOR GALLONS OF WATER PLUS ONE 94 Lb. SACK

COST IS: COST PER CUBIC FOOT OF SLURRY.

ND = NOT DETERMINED

THE CKD UTILIZED FOR ALL RESULTS IN THIS TABLE WAS SUPPLIED BY SOURCE I OF TABLE IV

TABLE III
APPROVED MATERIALS UTILIZED IN SLURRY MIXES
PRIOR ART FOR WELL SLURRY MEETING API SPECIFICATIONS

CEMENT	SILICA	WATER	DENSITY	COMPRESSIVE STRENGTH IN PSI	YEILD	COST
50%	50%	8	101.03	MEETS API SPECIFICATIONS	1.59	$2.32
50%	50%	9	98.23	MEETS API SPECIFICATIONS	1.72	$2.15

CEMENT TYPICALLY UTILIZED IS G SERIES PORTLAND CEMENT $75.00 PER TON
SILICA TYPICALLY UTILIZED IS A 200 MINUS SIEVE SPEC PRODUCT $82.50 PER TON

THESE SLURRY MIXES MEET API SPECIFICATION OF A HARD PLUG OF 1000 PSI COMPRESSIVE STRENGTH

COST IS: COST PER CUBIC FOOT OF SLURRY

TABLE IV
TYPICAL CHEMICAL ANAYLSIS FOR CEMENT KILN DUSTS

SOURCE OF CKD INGREDIENT	CEMENT KILN DUST SOURCE					
	I %	II %	III %	IV %	V %	VI %
SiO$_2$	12.3	17.19	17.61	9.9	22.4	14.6
Al$_2$O$_3$	3	4.34	4.25	3.1	10	3.4
Fe$_2$O$_3$	1.3	2.13	1.48	1.2	4.1	2.2
CaO	52.6	43.49	62.49	47.6	19.4	46.5
MgO	1.4	0.7	1.18	1.3	0.6	2
SO$_3$	3.7	1.34	8.79	0.9	10.1	5
Na$_2$O	0.1	0.43	ND	0.1	0.9	0.9
K$_2$O	2.4	1.44	2.86	1.1	14.1	5.1
LOSS ON IGNITION	23.3	29.6	ND	31.6	13.2	21.4
FREE LIME	16.9	ND	ND	ND	ND	ND

SOURCES IV, V, AND VI ARE EXAMPLES OF CKD WITH LARGE VARIATIONS OF SiO$_2$ AND CaO AS REPORTED IN U.S. PAT. NO. 4,432,800. THESE VARIATIONS DO NOT PRECLUDE THEIR USE IN THIS INVENTION.

FREE LIME: IDENTIFIED SEPERATLY IN CHEMICAL ANALYSIS BUT INCLUDED IN TOTAL FOR CaO.

ND = NOT DETERMINED